

INTERIOR FILLER IS 60



- > easy to process
- > for filling and smoothing
- > high whiteness
- > gypsum bound

Product description

Powdery, special, gypsum-bound wall and putty filler.

Only indoors as wall and putty filler for subsequent paint and wallpaper work, for filling cracks and small holes, for full area smoothing, for filling gypsum plasterboard.

Delivery format

Container	Outer packaging	Pallet
5 KG / KTN	-	84 KTN
1 KG / KTN	4	216 KTN

Storage

Can be stored frost-free, cool, and dry on wooden shelves in the unopened original container for 730 days

Processing

Recommended tools

Slow-rotating electric agitator, suitable mixing vessel, trowel, spatula, sponge board.

Mixing

Take a clean mixing vessel and add this product to water using a slow-rotating mixer until a homogeneous and lump-free blend is obtained (mixing time approx. 3 minutes).

Mixing ratio:

approx. 0.6 litres of water per 1 kg Murexin Interior Filler IS 60

Mix to a slightly thicker consistency to fill cracks and holes.

Processing

After a maturation time of approx. 2 minutes, apply and fill using a spatula or smoothing trowel. The pot life is heavily affected by the humidity and the temperature and lies at approx. 15 to 60 minutes. Small unevennesses must be fixed before hardening with a wet sponge board. Grindable after drying.

Technical data

Chemical base	gypsum
Bulk density	approx. 0.94 kg/l
Colour	white
Consumption	approx. 1 kg/m ² per mm of layer thickness
Layer thickness	max. 5 mm
Processing temperature	min. + 5°C / max. +30 °C
Water consumption	approx. 0.6 l/ kg (= 60%)
Setting time	approx. 60 min.
Fresh mortar thickness	approx. 1 kg/l

Substrate

Suitable substrates

The substrate must be dry, frost-free, solid, weight-bearing, dimensionally stable, free of dust, dirt, oil, grease, release agents and loose parts.

Suitable on all kinds of standard, mineral substrates, such as masonry, stone, plaster, concrete.

Only suitable on certain types of strongly absorbent substrates, aerated concrete, sandy or chalky substrates, for gypsum plasterboards in the joint area.

Not suitable on wood, plastic, metal, non-absorbent and water-repellent substrates as well as areas to be tiled, fresh concrete.

Product and processing instructions

Material information:

- If processing outside the ideal temperature and/or humidity range the material properties could change markedly.
- Bring the materials to the proper temperature before processing!
- In order to maintain the product properties, do not add any foreign materials!
- Water dosing quantities or dilution information must be strictly adhered to!
- Check tinted products for colour accuracy before application!
- Colour consistency can only be guaranteed within the same batch.
- The colour formation is significantly impacted by the environmental conditions.
- Powdery fillers are to be used immediately after opening the original packaging.
- Do not add water to plaster fillers which have already stiffened; clean mixing vessel before mixing again.
- Pores and cavities in concrete are to be filled in a separate step, particularly to prevent the formation of bubbles in the filler.

Environmental information:

- Do not process at temperatures below +5 °C!
- The ideal temperature range for the material, substrate and air is + 15 °C to + 25 °C.
- The ideal relative humidity range is 40% to 60%.
- Increased air humidity and/or lower temperatures may prolong the drying, setting and hardening time, while lower air humidity and/or higher temperatures will speed it up.
- Ensure adequate ventilation during the drying, reaction and hardening phase; avoid draughts!
- Protect against direct sunlight, wind and weather!
- Protect adjacent components!
- Increased air humidity as a result of plaster and screed work can lead to swelling and spalling of gypsum fillers.

Tips:

- We recommend using a test surface first or a small area for initial, small-scale testing.
- Please heed the product data sheets of all MUREXIN products used in the process.
- Keep a genuine original container of the respective batch for later repair work.

The information provided reflects average values that were obtained under laboratory conditions. Due to the use of natural raw materials, the indicated values of individual deliveries may vary slightly without impacting the product suitability.

Safety instructions

Please refer to safety data sheet for product-specific information with regard to composition, handling, cleaning, corresponding actions and disposal.

Limiting and monitoring exposure

Personal protective equipment:

General protection and hygiene measures:

- Common safety measures for handling chemicals are to be observed.
- Keep away from foodstuffs, beverages and feedstuffs.
- Take off contaminated, impregnated clothing immediately.
- Wash your hands before taking breaks and when finishing work.

Breathing protection:

- Filter P2.
- Wear breathing protection in case of inadequate ventilation.

Hand protection:

- The glove material must be impermeable and resistant to the product/substance/preparation.

Glove material

- Use gloves made from stable materials (e.g. nitrile).
- The selection of a suitable glove depends not only on the material, but also on other quality properties, which may vary from manufacturer to manufacturer.

Penetration time of the glove material

- The precise penetration time is to be found out from the protective glove manufacturer and complied with.

Eye protection: Protective goggles recommended when decanting.

Body protection: protective clothing.

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted.

Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction.

Please contact us if you have any reservations or doubt. This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.