

Professional White PW 400



Product description

Delivery format

Container	Outer packaging	Pallet
25 KG / KE	-	24 KE

Storage

Can be stored frost-free, cool, and dry on wooden shelves in the unopened original container for 365 days

Technical data

Chemical base	Synthetic resin dispersion
Density	approx. 1.6 g/cm ³
Colour	White; can be tinted with waterdilutable spot, base and tinting colours
Consumption	approx. 150 - 250 g/m ² per coat
Dilution	Water; first coat max. 20%, last coat max. 5% diluted
Drying time	after approx. 4 - 6 hrs. surface dry and paintable
Wet abrasion class	Class 3
Coverage	Class 2, at 8.2 m ² /l coverage
Gloss level	matt
Whiteness	73 (as per Berger)
Granulation	fine

Test certificates

Tested in accordance with (standard, classification ...)

ÖNORM EN 13300

Safety instructions

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted.

Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction. Please contact us if you have any reservations or doubt.

This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.