**Colour and Coating System** 

# AUSTRO NORM AN 750

- > ELF low emission and solvent-free
- > wash-resistant
- > ideal for improvement work

## **Product description**

High-coverage dispersion paint with high degree of whiteness. Ideal for improvements due to dull matt gloss and fine filling materials. Water-dilutable, low emission, and solvent-free. Wet abrasion: Class 3.

#### **Delivery format:**

Container	Outer packaging	Pallet
KE		85
KE		40
KE		24
KDO	10	350

#### Storage:

Can be stored frost-free, cool and dry on wooden shelves in unopened original container: 365 days

# Processing

#### **Recommended tools:**

Roller, brush, airless sprayer. Wash the tools with clean water after use.

#### **Processing:**

Murexin Austro Norm AN 750 can be applied by painting, rolling or spraying (also airless). Usually 1-2 applications are required. Due to the dull matt appearance and the fine grain, Austro Norm An 750 can be used for improvement work in wall and ceiling areas. Depending on the absorbency of the substrate, the primer can be diluted with 10 - 20% water. The topcoat is to be diluted with max. 5% water. For airless processing, we recommend using a 0.021" nozzle and 150 bar feed pressure.

### **Technical data**

Chemical base

Dilution

51035, AUSTRO NORM AN 750, valid from: 06.11.20
Gloss level
Colour
Density

Water; first coat max. 20%; dilute topcoat with max. 5% water Synthetic resin dispersion 1,6 kg/l white; can be tinted with spot, base and tinting colours stumpfmatt

020, Magdalena Riegler, Page 1





## Colour and Coating System



Consumption Wet abrasion class Coverage Whiteness Drying time Granulation approx. 150 - 250 g/m<sup>2</sup> per coat Klasse 3 Klasse 2, bei Reichweite 7,5 m<sup>2</sup>/l 75,1 (nach Berger) after approx. 4 - 6 hrs. surface dry and paintable fine

# **Test certificates**

**Tested in accordance with (standard, classification ...)** ÖNORM EN 13300

# Substrate

#### Suitable substrates:

Lime cement and cement plasters P Ic; P II; P III Lime cement and cement plasters P II & P III Gypsum and ready-mix plasters P IV & PV Plasterboards and gypsum plasterboards Concrete, aerated concrete Exposed masonry Weight-bearing old coats

The substrate must be dry, frost-free, solid, weight-bearing, dimensionally stable, free of dust, dirt, oil, grease, release agents and loose parts, and it must comply with the applicable technical national and European directives, standards and "generally accepted rules of the trade".

# For a perfect system

System products: Murexin Deep Primer LF 14, Murexin Special Insulating Primer SP 13

#### **Description:**

MUREXIN Deep Primer LF 14 for priming sandy and absorbent mineral substrates, such as concrete, gypsum, lime cement and cement plasters, gypsum and lime filler, gypsum plasterboards. Murexin Special Insulating Primer SP 13 for insulating marks and discolourations on absorbent substrates.

# **Product and processing instructions**

Material information:

- If processing outside the ideal temperature and/or humidity range the material properties could change markedly.
- Bring the materials to the proper temperature before processing!
- In order to maintain the product properties, do not add any foreign materials!
- Water dosing quantities or dilution information must be strictly adhered to!
- Carefully open the container, remove possible dry parts and shake the product well!
- Water-based systems have only a limited shelf life after dilution with water, which is why quick processing is recommended.
- Always work wet-in-wet to prevent deposits.
- The final wash or abrasion resistance is reached after approx. 28 days.

#### 51035, AUSTRO NORM AN 750, valid from: 06.11.2020, Magdalena Riegler, Page 2

## Colour and Coating System



Environmental information:

- The ideal temperature range for the material, substrate and air is + 15 °C to + 25 °C.
- The ideal relative humidity range is 40% to 60%.

- Increased air humidity and/or lower temperatures may prolong the drying, setting and hardening time, while lower air humidity and/or higher temperatures will speed it up.

- Ensure adequate ventilation during the drying, reaction and hardening phase; avoid draughts!
- Protect against direct sunlight, wind and weather!
- Protect adjacent components!
- Do not process at temperatures below 5 °C.

Tips:

- We recommend using a test surface first or a small area for initial, small-scale testing.
- Please heed the product data sheets of all MUREXIN products used in the process.
- Keep a genuine original container of the respective batch for later repair work.

- When using intensive, brilliant and dark colours, we recommend using the colour qualities of wet abrasion class  $\leq 2$  in at least "satin finish" (gloss level >15/60° MW) and first equalising the substrate in "white".

- In case of side lighting, we recommend using colour qualities of wet abrasion class ≤ 2 in "dull matt" (gloss level <5/85° MW).

The information provided reflects average values that were obtained under laboratory conditions. Due to the use of natural raw materials, the indicated values of individual deliveries may vary slightly without impacting the product suitability.

#### Safety instructions

Limiting and monitoring exposure

Personal protective equipment:

General protection and hygiene measures:

- Common safety measures for handling chemicals are to be observed.
- Keep away from foodstuffs, beverages and feedstuffs.
- Take off contaminated, impregnated clothing immediately.
- Wash your hands before taking breaks and when finishing work.
- Breathing protection: Only when spraying without sufficient extraction.

Hand protection: protective gloves.

Glove material

- The selection of a suitable glove depends not only on the material, but also on other quality properties, which may vary from manufacturer to manufacturer.

Penetration time of the glove material

- The precise penetration time is to be found out from the protective glove manufacturer and complied with.

Eye protection: Protective goggles recommended when decanting.

Body protection: protective clothing.

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted.

Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction. Please contact us if you have any reservations or doubt. This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.

51035, AUSTRO NORM AN 750, valid from: 06.11.2020, Magdalena Riegler, Page 3