

CARBOLINE BROWN BK 20

- > quick-drying
- > good weatherproofing



Product description

Tar-oil-free impregnating agent for exterior wood coatings. Good drying, high penetrability, good weatherproofing (pearling effect) and weather resistance.

Resistant to bacteria and fungus.

Stir the content of the container well, keep the container sealed tight after use. Remove dust, dirt, grease and wax from wood. Process with brush, roller or sprayer. Suitable for painting of hunter fences, pergolas, stakes, palisades, wooden sheds, etc.

Delivery format:

Container	Outer packaging	Pallet
5 L / KST		84
25 L / KST		24

Storage:

Can be stored frost-free, cool and dry on wooden shelves in unopened original container: 365 days

Processing

Recommended tools:

suitable painting tools

Mixing:

Stir the content of the container well.

Processing:

Processing can take place by painting, watering or spraying tunnel treatment. If possible, only dry wood with a moisture content of under 25% should be impregnated in order to achieve deeper penetration of the protection agent. Optimum processing temperature: +10 °C to +30 °C

Processing types:

SO = painting, spray tunnel treatment, brief immersion, flooding, but no manual spraying or splashing.

T = immersion (immersion time 20 minutes to several hours)

L = trough or adjustment impregnation (treatment time several hours to several days)

Technical data

Density	approx. 0.75 g/cm ³
Colour	natural brown
Viscosity	12 - 15 sec. in 4 mm DIN beaker (DIN 53211)
Gloss level	satin finish
Consumption	250 ml/m ² per coat
Drying time	Dry after approx. 2 hrs., fully dried after 12 - 24 hrs. (depending on the absorbency of the substrate and the coating quantity applied)
Solid body weight % bw	8 - 9 %

Substrate

Suitable substrates:

The max. wood moisture content is 15%. Woods which are rich in resin, especially tropical woods, are to be washed with cellulose thinner. For renewed coatings of the substrate, check suitability as a coating carrier. Remove non weight-bearing old paints, grind intact old paints. Grind defective spots down to the healthy wood. Clean again after grinding.

Product and processing instructions

Material information:

- If processing outside the ideal temperature and/or humidity range the material properties could change markedly.
- Bring the materials to the proper temperature before processing!
- In order to maintain the product properties, do not add any foreign materials!
- Water dosing quantities or dilution information must be strictly adhered to!
- Check tinted products for colour accuracy before application!
- Colour consistency can only be guaranteed within the same batch.
- The colour formation is significantly impacted by the environmental conditions.

Environmental information:

- Do not process at temperatures below +5 °C!
- The ideal temperature range for the material, substrate and air is + 15 °C to + 25 °C.
- The ideal relative humidity range is 40% to 60%.
- Increased air humidity and/or lower temperatures may prolong the drying, setting and hardening time, while lower air humidity and/or higher temperatures will speed it up.
- Ensure adequate ventilation during the drying, reaction and hardening phase; avoid draughts!
- Protect against direct sunlight, wind and weather!
- Protect adjacent components!

Tips:

- We recommend using a test surface first or a small area for initial, small-scale testing.
- Please heed the product data sheets of all MUREXIN products used in the process.
- Keep a genuine original container of the respective batch for later repair work.

The information provided reflects average values that were obtained under laboratory conditions. Due to the use of natural raw materials, the indicated values of individual deliveries may vary slightly without impacting the product suitability.

Safety instructions

Limiting and monitoring exposure

Personal protective equipment:

General protection and hygiene measures:

- Keep away from foodstuffs, beverages and feedstuffs.
- Take off contaminated, impregnated clothing immediately.
- Wash your hands before taking breaks and when finishing work.
- Breathing protection: Wear breathing protection in case of inadequate ventilation.

53495, CARBOLINE BROWN BK 20, valid from: 15.12.2020, Magdalena Riegler, Page 2

Colour and Coating System

Hand protection: protective gloves.

Glove material

- Butyl rubber
- Nitrile rubber

Penetration time of the glove material

- The precise penetration time is to be found out from the protective glove manufacturer and complied with.

Eye protection: tightly sealed protective goggles.

Body protection: protective clothing.

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted.

Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction. Please contact us if you have any reservations or doubt. This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.