

Nitro Thinner Oxylin AF 200

- > free of aromatic substances
- > high dissolving power
- > good cleaning effect



Product description

High quality cellulose thinner with high dissolving power. Free of aromatic substances. Suitable for Oxylin Nitro Enamel Paint as well as road marking paint.

Delivery format

Container	Outer packaging	Pallet
200 L / BFA	-	2 BFA
25 L / BKA	-	16 BKA
5 L / BKA	-	126 BKA
1 L / BKA	6	360 BKA

Storage

Can be stored frost-free, cool, and dry on wooden shelves in the unopened original container for 730 days

Processing

Processing

For diluting and cleaning.

Technical data

Flashpoint	below + 21 °C
Spec. weight	0,77 g/ml
Aromatics	none

Substrate

Suitable substrates

The substrate must be dry, frost-free, solid, weight-bearing, dimensionally stable, free of dust, dirt, oil, grease, release agents and loose parts, and it must comply with the applicable technical

53600, Nitro Thinner Oxylin AF 200, valid from: 27.01.2026, Nicole Zeiml, Page 1

Colour technology

national and European directives, standards and "generally accepted rules of the trade".

Rust and loose paint residues on metallic substrates are properly removed before application.

Loose paint residues on wooden substrates are removed mechanically. Greyed and weathered wooden surfaces are pre-treated down to the weight-bearing wooden substrate.

Product and processing instructions

Material information:

- If processing outside the ideal temperature and/or humidity range the material properties could change markedly.
- Bring the materials to the proper temperature before processing!
- In order to maintain the product properties, do not add any foreign materials!
- Water dosing quantities or dilution information must be strictly adhered to!
- Check tinted products for colour accuracy before application!
- Colour consistency can only be guaranteed within the same batch.
- The colour formation is significantly impacted by the environmental conditions.

Environmental information:

- Do not process at temperatures below +5 °C!
- The ideal temperature range for the material, substrate and air is + 15 °C to + 25 °C.
- The ideal relative humidity range is 40% to 60%.
- Increased air humidity and/or lower temperatures may prolong the drying, setting and hardening time, while lower air humidity and/or higher temperatures will speed it up.
- Ensure adequate ventilation during the drying, reaction and hardening phase; avoid draughts!
- Protect against direct sunlight, wind and weather!
- Protect adjacent components!

Tips:

- We recommend using a test surface first or a small area for initial, small-scale testing.
- Please heed the product data sheets of all MUREXIN products used in the process.
- Keep a genuine original container of the respective batch for later repair work.

The information provided reflects average values that were obtained under laboratory conditions. Due to the use of natural raw materials, the indicated values of individual deliveries may vary slightly without impacting the product suitability.

Safety instructions

Limiting and monitoring exposure

Personal protective equipment:

General protection and hygiene measures:

- Do not eat, drink, smoke or sniff while working.
- Preventive skin protection with skin protection cream.
- Common safety measures for handling chemicals are to be observed.
- Keep away from foodstuffs, beverages and feedstuffs.
- Take off contaminated, impregnated clothing immediately.
- Wash your hands before taking breaks and when finishing work.
- Avoid contact with the eyes and skin.

Breathing protection:

- Use a breathing filter device for short term or minor exposure; for more intensive or longer exposure, use a self-contained breathing apparatus.

Hand protection:

- Gloves / solvent-resistant.
- Protective gloves.

Glove material

- Nitrile rubber

- The selection of a suitable glove depends not only on the material, but also on other quality properties, which may vary from manufacturer to manufacturer.

Penetration time of the glove material

- The precise penetration time is to be found out from the protective glove manufacturer and complied with.

Eye protection: tightly sealed protective goggles.

53600, Nitro Thinner Oxylin AF 200, valid from: 27.01.2026, Nicole Zeiml, Page 2

TECHNICAL DATA SHEET

Colour technology

MUREXIN

Body protection: solvent-resistant protective clothing.

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted.

Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction. Please contact us if you have any reservations or doubt.

This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.